

## SW 2701 SERIES

### Twill Weave

### Available Colours

		Front	Back
Oyster	P12		
Oyster/Beige	P13		
Oyster/Pearl Gray	P14		
Oyster/Charcoal	P28		
Oyster/Pewter	P91		
Oyster/Chestnut	P92		

### Fabric Specifications

<b>Stock Widths</b>	63"/98"/126"
<b>Openness Factor</b>	1%
<b>Composition</b>	36% Fiberglass 64% Vinyl on Fiberglass
<b>Thickness</b>	.027"
<b>Weight</b>	14.6 oz/sq yrd
<b>Fire Rating</b>	NFPA 701-2004/CA US Title 19
<b>Cleaning Instructions</b>	Contact Manufacturer
<b>Spline</b>	Yes
<b>Railroaded</b>	Not Recommended

Styles 2701, 2703, 2705, and 2710 are vinyl coated fiberglass yarns woven into a traditional twill pattern which creates a two-sided fabric for the heat reduction benefit of light colors and the outward views and glare reduction of dark colors. Style 2701/2703/2705/2710 can also be used in exterior roller shades.

- ASTM E2180, ASTM 22 AATCC30 Part 3, ASTM G21, ASTM D3273, GREENGUARD Mold & Bacteria Standard ASTM 6329
- If you require additional fabric send E-mail to: [samples@frasershading.com](mailto:samples@frasershading.com)
- Actual fabric colours may vary from pictures, Fabric stock levels may vary.
- Openness factors are approximate. Mockups are recommended. Specification subject to change without notice. ©Fraser Shading Systems 2017



## SheerWeave 2701 1% Fenestration Properties

Description	Colour	S/C (Internal)						
		T <sub>s</sub>	R <sub>s</sub>	A <sub>s</sub>	T <sub>v</sub>	1/8" C/L	1/4" C/L	1/4" H.A.
P12	Oyster	21	64	15	17	0.36	0.36	0.33
P13	Oyster/Beige	15	57	28	12	0.38	0.38	0.34
P14	Oyster/Pearl Grey	8	54	38	4	0.40	0.39	0.34
P28	Oyster/Charcoal	5	39	56	6	0.49	0.47	0.39
P91	Oyster/Pewter	6	43	51	6	0.46	0.45	0.37
P92	Oyster/Chestnut	6	41	53	6	0.47	0.46	0.38

**KEY:** T<sub>s</sub> = Solar Transmittance, R<sub>s</sub> = Solar Reflectance, A<sub>s</sub> = Solar Absorption, T<sub>v</sub> = Visible Transmittance

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and the shading system.

Darker colours provide maximum glare reduction and visibility. For complete technical information, current test results, performance specifications and larger samples, contact FSS

### Specifications:

Composition:	36% Fiberglass, 64% Vinyl on Fiberglass
Openness factor:	Approximately 1%
Weight:	14.6 oz/yd <sup>2</sup> (495 g/m <sup>2</sup> )
Thickness:	.027 in (0.66mm)
Acoustical Value:	NRC .15 / SAA .15
Acoustical Performance:	NRC (Noise Reduction Coefficient) and SAA (Sound Absorption Average) tested in accordance with ASTM C423-09a.