FRASERSHADING









E SCREEN 3%

REENGUARD



70"/00"/122"



-03

Transparent

Available Colours

White/White	02.02	
White/Pearl	02.07	
White/Linen	02.20	
Linen/Linen	20.20	
Charcoal/Grey	30.01	
Charcoal/Charcoal	30.30	
Charcoal/Cocoa	30.61	
Charcoal/Apricot	30.71	
Cocoa/Cocoa	61.61	
Cocoa/Apricot	61.71	

Fabric Specifications

Stock Widths	/8"/98"/122"			
Openness Factor	3%			
Composition	36% Fiberglass 64% Vinyl			
Thickness	.017"			
Weight	11.6 oz/sq yrd			
Fire Rating	NFPA 701-04TM#1, California U.S. Title 19, CAN/ULC-S109 Small Flame Test			
Cleaning Instructio	ns	Contact Manufacturer		
Spline		Yes		
Railroaded		Not Recommended		

Mermet's "Fabrics for Life $^{\text{TM}}$ " begin with everyday life in mind, whether at home, in the office, hospitality or healthcare. Our state-of-the-art weaving process creates designer fabrics which function beautifully to maintain the view while efficientlymanaging the effects of the sun.

Mermet offers over 500 fabric options for interior and exterior applications, ranging from transparent, to translucent, to blackout. A variety of openness factors from 0% to 14% offer varying degrees of privacy, view through, glare control and heat protection.

Mermet's innovative, functional fabrics are designed for solar protection, energy savings, pleasing visual aesthetics and acoustical comfort. Mermet fabrics are GREENGUARD®certified and fire rated to NFPA 701 standards.

- Bacterial and Fungal Resistance: ASTM E2180 and ASTM G21
- If you require additional fabric send E-mail to: samples@frasershading.com
- Actual fabric colours may vary from pictures, Fabric stock levels may vary.
- Openness factors are approximate. Mockups are recommended. Specification subject to change without notice. ©Fraser Shading Systems 2017



E Screen 3% Fenestration Properties

						SHGC/G Value		
Description	Colour	T s	Rs	A s	Τv	CL-S	DG	
02.02	White/White	16	73	11	13	0.31	0.33	
02.07	White/Pearl	10	52	38	8	0.42	0.40	
02.20	White/Linen	16	63	21	12	0.37	0.37	
20.20	Linen/Linen	18	52	30	13	0.43	0.40	
30.01	Charcoal/Grey	5	10	85	5	0.66	0.54	
30.30	Charcoal/Charcoal	5	4	91	4	0.70	0.56	
30.61	Charcoal/Cocoa	4	7	89	3	0.68	0.55	
30.71	Charcoal/Apricot	7	18	75	7	0.62	0.51	
61.61	Cocoa/Cocoa	5	9	86	5	0.67	0.54	
61.71	Cocoa/Apricot	7	19	74	6	0.61	0.51	

KEY: The fenestration property tests were conducted in accordance with EN 14501:2005, ASTM 891, ASTM E903-96: Shading Coefficient (SC), Solar Heat Gain Coefficient (SHGC), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance(As), Visible Light Transmittance (Tv); ¼ (6mm) Clear Glass (CL); 4mm Clear Glass, Single Glazing (CL-S); Double Glazing 4mm/16mm/4mm with low E-coating in position 3, space filled with Argon (DG); To calculate shading coefficient: SHGC CL-S / 0.87. Acoustical performance tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. The above data is indicative.

ph: 604-881-4881

fx: 604-881-4882

Specifications:

Composition: 36% Fiberglass / 64% Vinyl

Openness factor: Approximately 3%

Weight: 11.6 oz / yd2 (393 g / m2) + 5%

Thickness: .017" (0.43 mm) + 5% Accoustical Performance: NRC: 0.15, SAA: 0.17